

Solid electrolyte membrane based on poly(arylene ether sulfone)-g-poly(ethylene glycol)  
with various end groups for Lithium-ion battery

티엔전환, 김덕준<sup>†</sup>  
성균관대학교  
(djk@skku.edu<sup>†</sup>)

In this study, the solid-state polymer electrolyte membrane with high lithium-ion conductivity and lithium-ion transference number was prepared from poly(arylene ether sulfone) grafted with various end-group functionalized poly(ethylene glycol). PEG plays the role of lithium ion conductor by segmental motion, but the crystallinity of PEG disturbs the conduction of lithium-ion. In this report, the end group of PEG was modified to reduce the crystallinity and improved lithium salt solvation. So that the lithium-ion conductivity and transference number can be improved. Among the prepared membranes, the PAES-g-PEG with A-type end group showed the highest room-temperature lithium-ion conductivity of  $8.97 \times 10^{-4} \text{ S cm}^{-1}$  and lithium-ion transference number of 0.4 resulting in the improvements in full solid-state lithium battery performance.